

Quality Paints since 1845
MATHYS[®]



PEGALINK[®]

Univerzalni temeljni premaz za bolje prijanjanje

- Izvrsno prijanjanje na većini površina
- Elastičan i UV otporan
- Izvrsno razlivanje

WWW.MATHYSPAINTS.EU

OPIS

Univerzalni adhezijski temeljni premaz na bazi akrilnih smola dispergiranih u vodi.

PREPORUČENA UPOTREBA

Prianjanje na mnoge površine: drvo, gips, cement, cigle i posebno na glatke i teško prianjajuće površine kao što su: pocinčani čelik, bakar, cink, polikarbonat, tvrdi PVC, Pegagraff Hydro itd. Može se koristiti na unutarnjim i vanjskim površinama.

TEHNIČKI PODACI

Gustoća (g/cm ³):	1,2 - 1,3
Stupanj sjaja:	Saten
Stupanj sjaja pri 60°:	Saten: ± 20%
Suha tvar (težinski):	± 52 %
Suha tvar (volumno):	± 37 %

VRIJEME SUŠENJA PRI 20°C/RV50%

Suh na dodir:	20 minuta
Suh za obradu:	1 sat
Suh za bojenje:	24 sata bojama na bazi vode. Dekorativne alkidne lakove treba prvo testirati na manjoj površini radi provjere prionjivosti.
Potpuno suh:	2 dana

PREPORUČENA DEBLJINA MOKROG FILMA

100 µm

PREPORUČENA DEBLJINA SUHOG FILMA

36 µm

TEORETSKA POTROŠNJA

± 10 m²/l

PRAKTIČNA POTOŠNJA

Praktična potrošnja ovisi o mnogim čimbenicima kao što su poroznost i hrapavost podloge te gubicima materijala tijekom nanošenja.

PRIPREMA POVRŠINE

Uglavnom nije potrebno brusiti mat površine; u većini slučajeva čišćenje i odmaščivanje površine potrebno je u svrhu postizanja boljeg prianjanja.

UPUTE ZA KORIŠTENJE

Kako bi se osigurala homogenost, materijale za premazivanje potrebno je temeljito promiješati prije upotrebe.

UVJETI ZA PRIMJENU

> 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

All types can be used. Do not dilute.

APPLICATION & THINNING: ROLLER

Not recommended, except with a lacquer roller. Do not dilute

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 11 / Pressure: 200 bars. Do not dilute.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Possible, do not dilute.

CLEANING OF EQUIPMENT / SPILLS

Water.

REMARKS

Adhesion cross-cut intact on the above-mentioned surfaces.

In case of doubt, f.i. on a substrate which has not been mentioned, an adhesion test has to be done after 2 days of drying, especially on old paints.

SAFETY DATA

VOC level:	45 g/l
VOC readymix:	45 g/l
VOC category:	A/i
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 21/06/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu